



## PULL-OUT STRENGTH TEST



<u>SIZE &amp; LENGTH</u>	<u>THREAD LENGTH*</u>	<u>REDWOOD</u>	<u>CEDAR</u>	<u>PRESSURE TREATED</u>
(.169) #8 X 1-3/8"	1"	600 LBS.	344 LBS.	317 LBS.
(.169) #8 X 1-3/4"	1"	600 LBS.	344 LBS.	317 LBS.
(.169) #8 X 2"	1"	600 LBS.	344 LBS.	317 LBS.
(.185) #9 X 2-1/4"	1-1/4"	617 LBS.	384 LBS.	357 LBS.
(.185) #9 X 2-1/2"	1-1/4"	617 LBS.	384 LBS.	357 LBS.
(.185) #9 X 3"	1-1/2"	705 LBS.	421 LBS.	419 LBS.
(.20) #10 X 3-1/4" (DOCK)	1-1/2"	886 LBS.	569 LBS.	509 LBS.
(.20) #10 X 3-3/4"	2"	1,111 LBS.	802 LBS.	794 LBS.
(.20) #10 X 4-1/2"	2-1/2"	1,472 LBS.	1,138 LBS.	1,146 LBS.
(.20) #10 X 5"	2-1/2"	1,472 LBS.	1,138 LBS.	1,146 LBS.
(.20) #10 X 6"	2-1/2"	1,472 LBS.	1,138 LBS.	1,146 LBS.

\* NOTE: Test results in pounds reflect penetration into materials noted at same embedment as the thread length of each size screw tested.

---

Faspac, Incorporated  
13909 NW 3<sup>rd</sup> Court  
Vancouver, Washington 98685

---

Telephone: (360) 573-7565  
Toll Free: (800) 847-4714  
Fax: (360) 573-7939  
Toll Free: (800) 547-7492